



## OK Autrod 410

A continuous solid welding wire of 13% Cr type. OK Autrod 410 is used for welding of similar martensitic and martensitic-ferritic steels in different applications. OK Autrod 410 can be used in combination with OK Flux 10.93.

<b>Classifications Wire Electrode</b>	SFA/AWS A5.9 : ER410
---------------------------------------	----------------------

<b>Alloy Type</b>	Martensitic-ferritic (13 % Cr)
-------------------	--------------------------------

### Typical Wire Composition %

<b>C</b>	<b>Mn</b>	<b>Si</b>	<b>Cr</b>
0.12	0.5	0.3	12.2