

## Shield-Bright 308L

Shield-Bright 308L was developed for welding type 304L stainless steel and can also be used for welding types 301, 302, and 304 steels. It may also be used for welding types 321 and 347 if the service conditions do not exceed an approximate of 750°F (399°C).

<b>Approvals</b>	CWB AWS A5.22 E308LT1-1 E308LT1-4 VdTUV 04832 (M20 M21) LR 304L (C1) KR RW308LG (C) (C1) DNV NV 308L (C1) ClassNK KW308LG(C) (C1) CCS 308L (C1) ABS E308LT1-1 (C1) CE EN 13479
------------------	--

Approvals are based on factory location. Please contact ESAB for more information.

<b>Welding Current</b>	DC+
<b>Alloy Type</b>	C Cr Ni
<b>Shielding Gas</b>	M21, C1 (EN ISO 14175)

### Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
<b>M21 Shielding Gas</b>			
As Welded	410 MPa (59 ksi)	580 MPa (84 ksi)	44 %
<b>C1 Shielding gas</b>			
As Welded	372 MPa (54 ksi)	568 MPa (82 ksi)	61 %

### Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
<b>C1 shielding gas</b>		
As Welded	-29 °C (-20 °F)	60 J (44 ft-lb)
As Welded	-196 °C (-321 °F)	30 J (22 ft-lb)

### Typical Weld Metal Analysis %

C	Mn	Si	S	P	Ni	Cr
0.025	1.10	0.70	0.007	0.025	10.0	19.1

### Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.2 mm (0.045 in.)	130-220 A	24-29 V	5.8-14.4 m/min (228-567 in./min)	1.9-4.6 kg/h (4.2-10. lb/h)